



The WPC ambient with **PCI** (Permanent Change Indicator) is a two-layer field-joint coating system for pipeline operating at ambient temperature.

### Product description

**WPCT, WPC/B, WPC-B30, WPC-C30 field-joint coatings.**

**Construction:** Two-layer system:

**First layer:** Visco-elastic low preheat sealant adhesive.

**Second layer:** Radiation cross-linked, high density polyethylene with **PCI** (Permanent Change Indicator)

WPC ambient is a wrap-around heat-shrinkable, ready-to-fit assembly for the corrosion protection of field girth weld joints in distribution and transmission networks, for use especially in low shear or low stress environments and in moderate climates. (Above pipe diameter DN500 (20") in high shear and high stress environments, the use of WPC-C50,

HTLP60 is recommended or contact a Tyco Adhesives representative).

WPC ambient is compatible with standard pipe coatings. WPC ambient can also be used for coating bare, replacement pipe sections and large radius bends. The system is designed to be applied with minimum preheating of the pipe.

The installation is carried out directly on the cleaned and pre-heated pipe surface without any primer being required. During installation, the heat-shrinkable sleeve is wrapped around and shrunk to form a tight fit around the joint. During recovery, the adhesive softens and flows to form a perfect bond with the pipe surface providing protection against corrosion. The radiation cross-linked outer layer forms a tough barrier against mechanical damage and moisture transmission.

### Product features/benefits

- Dimpled backing provides a "permanent change" indicator for application of heat**  
 Ensures correct application heat & allows easy post-heat inspection. Reliable inspectability at any time.
- Low preheat sensitivity & proven functionality**  
 Installation friendly in combination with high functional performance.
- High impact and penetration resistance**  
 Tough, but flexible even at low temperatures!
- Available as all-in-one unit or roll form**  
 Saves money by keeping inventory and logistics costs low.
- Sealing adhesive automatically flows and repairs minor mechanical damages**  
 "Self-healing effect". Saves extra intervention steps.
- No special equipment or skills required**  
 Makes installation fast and easy. Keeps installation costs low.

### Product selection guide

	WPCT	WPC/B	WPC-B30	WPC-C30
<b>Max operating temperature</b>	30°C (86°F)	30°C (86°F)	30°C (86°F)	30°C (86°F)
<b>Compatible line coatings</b>	PE, FBE, Coal Tar, Tape & Asphalt	PE, FBE, Coal Tar, Tape & Asphalt	PE, FBE, Coal Tar, Tape & Asphalt	PE, FBE, Coal Tar, Tape & Asphalt
<b>Min preheat temperature</b>	60°C (140°F)	60°C (140°F)	60°C (140°F)	60°C (140°F)
<b>Recommended pipe preparation</b>	ST2½ - ST3 or SA 2½	ST2½ - ST3 or SA 2½	ST2½ - ST3 or SA 2½	ST2½ - ST3 or SA 2½
<b>Soil stress restrictions</b>	Moderate	Moderate	Moderate	Moderate
<b>Performance</b>	EN 12068 class B30	EN 12068 class B30	EN 12068 class B30	EN 12068 class C30

### Product thickness

	WPCT	WPC/B	WPC-B30	WPC-C30
Backing (as supplied)	0.022 in. (0.55 mm)	0.030 in. (0.76 mm)	0.030 in. (0.76 mm)	0.040 in. (1.0 mm)
Backing (fully free recovered)	0.030 in. (0.76 mm)	0.040 in. (1.0 mm)	0.040 in. (1.0 mm)	0.055 in. (1.4 mm)
Mastic sealant (as supplied)	0.055 in. (1.4 mm)	0.060 in. (1.5 mm)	0.047 in. (1.2 mm)	0.060 in. (1.5 mm)

### Product properties: WPC ambient (1)

Property	Test method	WPCT	WPC/B	WPC-B30	WPC-C30
		Typical Value			
<b>Backing</b>					
Tensile strength	ASTM D-638	3000 psi (20 MPa)	3000 psi (20 MPa)	3000 psi (20 MPa)	3000 psi (20 MPa)
Elongation	ASTM D-638	580%	580%	580%	580%
Hardness, Shore D	ASTM D-2240	55	55	55	55
Shrink force	ASTM D-638	40 psi	40 psi	40 psi	40 psi
	150°C (302°F)				
Dielectric strength	ASTM D-149	500 volts/mil	500 volts/mil	500 volts/mil	500 volts/mil
		20 kV/mm	20 kV/mm	20 kV/mm	20 kV/mm
Water absorption	ASTM D-570	0.05%	0.05%	0.05%	0.05%
<b>Adhesive</b>					
Softening point	ASTM E-28	90°C (194°F)	90°C (194°F)	92°C (198°F)	92°C (198°F)
Lap shear	ASTM D-1002	35 psi	35 psi		
	EN 12068				
	@ 10 mm(0.4")/min.	22 N/cm <sup>2</sup>	22 N/cm <sup>2</sup>	8 N/cm <sup>2</sup>	8 N/cm <sup>2</sup>

## Product properties: WPC ambient (2)


Property	Test method	WPCT	WPC/B	WPC-B30	WPC-C30
		Typical Value			
<b>Sleeve</b>					
Peel to Steel	ASTM D-1000 EN 12068 @ 10mm (0.4")/min.	14 lbs/in.width 1.6 N/mm	14 lbs/in.width 1.6 N/mm	0.9 N/mm	0.9 N/mm
Cathodic disbondment	EN 12068, 30 days	8 mm radius	8 mm radius	9 mm radius	9 mm radius
Impact resistance	ASTM G-14 EN 12068	35 in-lbs > 8 Nm	50 in-lbs > 8 Nm	> 8 Nm	> 15 Nm
Penetration resistance	ASTM G-17  EN 12068 class B30 (1 N/mm <sup>2</sup> ) class C30 (10 N/mm <sup>2</sup> )	> 0.6 mm *	> 0.6 mm *	> 0.6 mm *	> 0.6 mm *

\* Remaining coating thickness

## Ordering information

### WPCT, WPC/B and WPC-C30 type products are available:

- as Uni-sleeve (pre-cut sleeve with pre-attached closure patch)
- as a roll (closure patches to be ordered separately)



Select sleeve width that will overlap onto the mill-applied coating by 2 inches (50 mm) minimum on each side of the weld joint.  
Take a 10% shrinkage during installation of sleeve width into account when calculating the minimum sleeve width.

### WPC-B30 type products are only available

- as a roll (closure patches to be ordered separately)

### \* Cut piece / Uni-sleeve

Example: WPCT-10750X17/UNI - WPC-10750X17/B/UNI - WPC-C30-DN250-450

		Standard Ordering options
WPC...	Product type	WPCT, WPC/B, WPC-C30
10750	Outside pipe diameter in mils	2.375" – 68.000" <sup>(1)</sup>
DN250	Pipe diameter in DN	DN50 – DN 1700 <sup>(1)</sup>
17	Sleeve width in inches (Sw)	11" (285 mm) <sup>(2)</sup> , 17" (450 mm) <sup>(2)</sup> , 24" (600 mm) <sup>(2)</sup> , 34" (870 mm) <sup>(2)</sup>
450	Sleeve width in mm (Sw)	17" (450 mm) <sup>(2)</sup> , 24" (600 mm) <sup>(2)</sup>
/UNI	Designates pre-attached closure patch	optional

<sup>(1)</sup> Above pipe diameter 20" (DN500) in high shear and high stress environments, the use of WPC-C50, HTLP60 or others are recommended.

<sup>(2)</sup> Nominal width

### \* Roll form (closure patches to be ordered separately)

Example: WPCT-17x100-RL

		Standard Ordering options
WPC...	Product type	WPCT, WPC/B, WPC-B30, WPC-C30
17	Roll width in inches (Sw)	11" (285 mm) <sup>(1)</sup> , 17" (450 mm) <sup>(1)</sup> , 24" (600 mm) <sup>(1)</sup> , 34" (870 mm) <sup>(1)</sup>
100	Roll length in feet (Sl)	100 ft (= 30 m), 66 ft (= 20 m, for C30/width 34" (870 mm) only)

### \* Closure patch

Example: WPCP-IV-4x17

4	Closure patch width in inches (Pw)	4" (100 mm), 5" (125 mm), 6" (150 mm), 8" (200 mm)
17	Closure patch length in inches (PI)	11" (285 mm) <sup>(1)</sup> , 17" (450 mm) <sup>(1)</sup> , 24" (600 mm) <sup>(1)</sup> , 34" (870 mm) <sup>(1)</sup>

Sleeve cut lengths and appropriate closure patch widths depend on the pipe size and product construction, see application table AT-GIRTHWELD-REV-2-08/01.

For proper product installation, see latest installation instruction.

Tyco Adhesives warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the technical data sheet when used in compliance with Tyco Adhesives' written instructions. Since many installation factors are beyond our control, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection therewith. Tyco Adhesives' liability is stated in the standard terms and conditions of sale. Tyco Adhesives makes no other warranty either expressed or implied. All information contained in this technical data sheet is to be used as a guide and is subject to change without notice. This technical data sheet supersedes all previous data sheets on this product.

**Tyco**  
**Adhesives**  
Corrosion Protection Group  
[www.TycoAdhesives.com](http://www.TycoAdhesives.com)

**Headquarters:**  
Tyco Adhesives  
1400 Providence Hwy  
Norwood, MA 02062 USA  
Int'l Tel: +1 781 440-6161  
US Toll Free: +1 800 248-0149  
Fax: +1 781 440-6271  
E-mail: CPG@TycoAdhesives.com

**In Europe, Middle East, Africa, Asia & Pacific:**  
Tyco Adhesives B.V.B.A.  
Nieuwlandlaan B15  
B-3200 Aarschot, Belgium  
Tel: +32 16 55 36 00  
Fax: +32 16 55 36 74  
E-mail: CPG@TycoAdhesives.com

**In the Americas:**  
Tyco Adhesives L.P.  
1675 Suite C Brandywine Avenue  
Chula Vista, CA 91911 USA  
TEL: Mexico +52 (66) 23-34-33  
TEL: US +1 (619) 4 24 42 59  
FAX: Mexico +52 66 23-64-63  
FAX: US +1 (619) 4 24 42 58  
E-mail: CPGTJ@TycoAdhesives.com

Local agent / Distributor: